



marcstone

CUSTOM ARCHITECTURAL STONE CASTING

P.O. Box 52, Hampton MN 55031
Office 651-437-7972 | Bids@Marcstone.com

WASHING

Marcstone cast stone is designed to receive

a final masonry wash. Use a masonry wash product.

We recommend these three, in this order: Prosoco Sure Klean® Custom Masonry Cleaner, Prosoco Sure Klean® 101 Lime Solvent, or Prosoco Sure Klean® 600.

No white residue is present when using 101 Lime and Custom Masonry Cleaner. Sure Klean 600 can leave a white haze, especially on darker colors, that can be removed with a more thorough rinse along with a brush.



Prosoco® Sure Klean®
Custom Masonry Cleaner



Prosoco® Sure Klean®
101 Lime Solvent



Prosoco® Sure Klean®
600

APPLICATION INSTRUCTIONS:

- 1** Always pre-wet surface with clean water, working from the bottom to the top. On vertical surfaces, keep lower areas wet to avoid streaks.
- 2** Apply prediluted cleaner directly to surface from the bottom up using a masonry brush or low-pressure spray.
- 3** Leave cleaner for 2–5 minutes. Do not let cleaner dry into the surface. If surface begins to dry, reapply cleaner.
- 4** Reapply cleaner and remove any heavy buildup of excess mortar using a wooden scraper or piece of brick. Take care not to harm masonry surface.
- 5** Working from bottom to the top, rinse thoroughly with fresh water. If pressure rinsing equipment is not available, brush the surface while rinsing.
- 6** Reapply as needed following steps 1–5.



OUR CAST STONE IS DESIGNED TO BE
**INCLUDED IN THE
MASONRY WASH!**

TOPICAL SEALER

- 7** As a final protectant where salt is prevalent, Marcstone recommends sealing with a topical masonry sealer such as Prosoco Sure Klean® Weather Seal Natural Stone Treatment WB Plus or similar.



Prosoco® Sure Klean®
Weather Seal Natural
Stone Treatment

